

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

MECCANICA

ECOLOGIA

CERAMICA

ALIMENTARE

TECHNICAL DATA SHEET

Results of tests performed on the ceramic tiles manufactured by **RONDINE S.p.A** denominated **SERIE ECOWOOD GRIP** are listed in the following tables:

CHARACTERISTICS (TEST METHOD)	REQUIREMENTS EN14411:2012- G	RESULTS	TEST REPORT
DETERMINATION OF WATER ABSORPTION (ISO 10545-3) (%)	Average value $E \leq 0,5$	0,3	201122961
BREAKING STRENGTH (ISO 10545-4) (N)	≥ 1300	1583	2011229610
DETERMINATION OF MODULUS OF RUPTURE (N/mm ²) (ISO 10545-4)	≥ 35 / N.A.	N.A.	2011229610
RESISTANCE TO ABRASION (ISO 10545-7)	Abrasion class and cycles passed		ABRASIONE
DETERMINATION OF CHEMICAL RESISTANCE (GL) (ISO 10545-13)	Declared value (low and high concentration acids and alkalis) Minimum class B to household chemicals and swimming pool salts	A (low and high concentration acids and alkalis) A (household chemicals and swimming pool salts)	201122964
RESISTANCE TO STAINING (ISO 10545-14)	Minimum Class 3	5	201122965

CHARACTERISTICS (TEST METHOD)	REQUIREMENTS UNI EN 176	RESULTS	TEST REPORT
DETERMINATION OF MOHS HARDNESS	Glazed tile minimum 5	8	201122962

CHARACTERISTICS (TEST METHOD)	REQUIREMENTS CERAMIN TILE INSTITUTE	RESULTS	TEST REPORT
DETERMINATION OF STATIC COEFFICIENT OF FRICTION ASTM C1028	$>0,60$	DRY 0,78 WET 0,70	201122966

CHARACTERISTICS (TEST METHOD)	REQUIREMENTS ANSI A137.1:2012 Version 1	RESULTS	TEST REPORT
DETERMINATION OF DYNAMIC COEFFICIENT OF FRICTION BOT 3000	$>0,42$		DCOF

CHARACTERISTICS (TEST METHOD)	REQUIREMENTS DIN	RESULTS	TEST REPORT
DETERMINATION OF SLIPPERINESS (DIN 51130:2014)	Reported value	27,0° R11	201122967
DETERMINATION OF SLIPPERINESS (DIN 51097:1992)	Reported value		DIN

CHARACTERISTICS (TEST METHOD)	REQUIREMENTS B.C.R. Rep. CEC 6/81	RESULTS	TEST REPORT
DETERMINATION OF SLIPPERINESS (D.M. 236 - 89 Rif.B.C.R.)	$>0,40$	DRY 0,79 WET 0,73	201122969