

1. Properties and process features

Porcelain stoneware classifiable, according to standard EN14411, as group BIa.

Frost-proof slabs that resists chemical attacks, achieved through dry-forming of high-quality bodies made up of natural raw materials (kaolin minerals, feldspars), atomised, mixed. The slabs are made mechanically resistant through a sintering process at very high temperatures.

2. Compliance with Standards

In compliance with the requirements of the European standards EN14411 and International ISO13006 Annex G

EN ISO 10545.3 -(water absorption) (resistance to deep abrasion) EN ISO 10545.6 -(coefficient of linear thermal expansion) EN ISO 10545.8 -EN ISO 10545.9 -(resistance to thermal shocks) EN ISO 10545.12 -(resistance to frost) EN ISO 10545.13 -(resistance to chemicals) EN ISO 10545.14 (resistance to stains) and must ensure compliance with DIN 51094 (color resistance to light).

The maintenance of aforesaid features must be ensured by the Quality Control System implemented by the company in accordance with standard UNI-EN ISO 9001:2015.

Slabs, with a low environmental impact, obtained by pursuing policies of continuous improvement aimed at reducing the wastes of non-renewable resources by using raw materials often found in nature, through the adoption of an Environmental Management System certified in accordance with standard **UNI-EN ISO 14001:2015** and/or registration to the "ECO-MANAGEMENT" Community system, in accordance with the provisions of *EMAS* Regulations.

3. Commercial Description of Product

COMPANY	Ariostea
COLLECTION	ULTRA_BLEND.HT
FINISH	Soft – Polished Silk
SIZE mm	1000x1000
THICKNESS mm	6,0

Completely vitrified materials belonging to Group BIa Meets requirements of standard EN 14411 Annex G-UGL.



DIMENSIONS:

Materials supplied in caliber 0 (Mono-caliber).

Nominal	Average production	
dimensions mm	dimensions mm	
1000 x 1000	1000 x 1000	

COLORS:



4. Technical features and product brands

TECHNICAL FEATURES		MEASURING STANDARDS	AVERAGE VALUE
		OR METHOD	
7	SIZES	ISO 10545.2	± 0.1% Length and width ± 5% Thickness ± 0.1% Edge straightness ± 0.1% Orthogonality ± 0.2% Flatness
J	WATER ABSORPTION	ISO 10545.3	≤ 0,1%
+	MODUL OF ROPTURE (R)	ISO 10545.4	48 N/mm ²
()	RESISTANCE TO DEEP ABRASION	ISO 10545.6	140 mm ³
← •→	COEFFICIENT OF LINEAR THERMAL EXPANSION	ISO 10545.8	6,5 x 10 ⁻⁶ °C ⁻¹
The state of the s	RESISTANCE TO THERMAL SHOCKS	ISO 10545.9	Resistant
	RESISTANCE TO FROST	ISO 10545.12	Conforms
	RESISTANCE TO CHEMICALS	ISO 10545.13	Conforms
*	COLOR RESISTANCE TO LIGHT	DIN 51094	Unaffected
	FIRE PROOF	Decision 96/603 CE not requested	Class A1 - A1 _{FL}

 09^{th} November 2018