

TECHNICAL FEATURES	
Collection: Level stone natural rectified slabs Surface: Natural	Brand: Level
Size (cm): 160X320	Thickness (mm): 6,5

Compliant with standard EN 14411:2016 annex G group Bla - GL

Compliant with standard ISO 13006:2018 annex G group Bla - GL

Technical Features	Testing Method	Meas. unit	Average Typical Values	Established limits
DIMENSIONAL PROPERTIES AND SURFACE QUALITY				
Dimensions				Nominal Length of edge N (cm) 7≤N<15 Nominal Length of edge N (cm) N≥15
Length and width (*)	ISO 10545-2	(mm) (%)	Complies with the standards	±2% (max 5mm) ±2% (max 5mm) ±2% (max 5mm)
Length and width (**)				
Not Rectified				
Rectified			Complies with the standards	±0,9 mm ±0,6% ±2,0 mm
Thickness				
Not Rectified				
Rectified			Complies with the standards	±0,4 mm ±0,3 % ±1,0 mm
Straightness of sides				
Not Rectified				
Rectified			Complies with the standards	±0,5 mm ±5% ±0,5 mm
Rectangularity				
Not Rectified				
Rectified			Complies with the standards	±0,5 mm ±5% ±0,5 mm
Surface Flatness c.c - e.c. - w.				
Not Rectified				
Rectified			Complies with the standards	±0,75 mm ±0,5 % ±1,5 mm
Surface Quality			Complies with the standards	±0,4 mm ±0,3 % ±0,8 mm
				±0,75 mm ±0,5% ±2,0 mm
				±0,4 mm ±0,3% ±1,5 mm
				±0,75 mm ±0,5% ±2,0 mm
				±0,6 mm ±0,4% ±1,8 mm
			Complies with the standards	≥95%
PHYSICAL PROPERTIES				
Water absorption	ISO 10545-3	(%)	≤ 0,5	Eb ≤ 0,5 (Individual maximum value 0,6%)
Water absorption	ASTM C373-14	(%)	≤ 0,5	
Modulus of rupture	ISO 10545-4	(N/mm ²)	≥ 35	R ≥ 35 (Individual minimum value 32 N/mm ²)
Breaking Strength	ISO 10545-4	(N)	≥ 700	≥1300 (Thickness ≥7,5 mm) ≥700 (Thickness < 7,5 mm)
Resistance to surface abrasion	ISO 10545-7		See attached table	Abrasion class and cycles passed
Linear thermal expansion coefficient	ISO 10545-8	(x(10)-6/°C)	≤ 9	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)
Thermal shock resistance	ISO 10545-9		Complies with the standards	Declared value (EN 14411:2016) **** Test Method available (ISO 13006:2018)
Crazing Resistance	ISO 10545-11		Complies with the standards	Pass according to EN ISO 10545-1 (EN 14411:2016) Required (ISO 13006:2018)
Frost resistance	ISO 10545-12		Complies with the standards	Pass according to EN ISO 10545-1 (EN 14411:2016) Required (ISO 13006:2018)
Colour resistance to light exposure	DIN 51094		Complies with the standards	No sample must show noticeable colour modifications.

TECHNICAL FEATURES	
Collection: Level stone natural rectified slabs Surface: Natural	Brand: Level
Size (cm): 160X320	Thickness (mm): 6,5

Technical Features	Testing Method	Meas. unit	Average Typical Values	Established limits
CHEMICAL PROPERTIES				
Resistance to chemicals for household use and swimming pool salts	ISO 10545-13		A	GB Minimum (EN 14411:2016) GB Minimum (ISO 13006:2018)
Resistance to low concentrations of acids and alkalis	ISO 10545-13		LA	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)
Resistance to high concentrations of acids and alkalis	ISO 10545-13		HA	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)
Chemical Resistance	ASTM C650-04		Not Affected	Declared value (ANSI A137.1-2012)
Stain resistance	ISO 10545-14		Class 5	Minimum class 3 (EN 14411:2016) Minimum class 3 (ISO 13006:2018)

ANTISLIPPERY PROPERTIES				
Slipperiness Resistance: Ramp Method	DIN 51130 DGUV Regel 108-003		R9	from R9 to R13
Slipperiness Resistance: B.C.R.	D.M. N.236 14/6/89		$\mu > 0,40$	$\mu > 0,40$
Dynamic coefficient of friction (DCOF)	ANSI A326.3:2017		$>0,42$	$\geq 0,42$

* The work size shall be chose, for non-modular tiles, so that the difference between the work size and the nominal size is:

** The deviation, in percent, of the average size for each tile (2 or 4 sides) from the work size..

**** See Table 2 for uses where it is applicable

c.c. Centre curvature, related to diagonal calculated from the work sizes

e.c. Edge curvature, related to the corresponding work sizes.

w. Warpage, related to diagonal calculated from the work sizes.

TECHNICAL FEATURES

Collection: Level stone natural rectified slabs Surface: Natural	Brand: Level
Size (cm): 160X320	Thickness (mm): 6,5

Resistance to surface	abrasion - ISO 10545-7
Dark colors	Class 4 - Visible abrasion after 2100 cycles
Light colors	Class 5 - Visible abrasion after > 12000 cycles